




ADVANTAGES OF FRC CSD-2500 STEEL FIBERS:

- Requires no minimum amount of concrete cover
- Always positioned in compliance with codes
- Safe and easier to use than traditional reinforcement
- Reduces construction time
- Leads to uniform application of Shotcrete thickness
- No voids that can develop behind wire mesh

FRC CSD-2500 STEEL FIBERS

FRC CSD-2500 steel fibers are designed specifically for the reinforcement of concrete and shotcrete mixes. FRC CSD-2500 is a cold drawn undulated steel fiber, to provide optimum anchorage within the concrete. FRC CSD-2500 steel fibers are specifically designed to meet or exceed the defined performance requirements. FRC CSD-2500 is private labeled for FRC Resources and meets the same codes and standards as SikaFiber Novocon XR.

FEATURES & BENEFITS

- High tensile strength fiber bridging joints and cracks to provide tighter aggregate interlock resulting in increased load-carrying capacity
- Provides uniform multi-directional concrete reinforcement
- Increases crack resistance, ductility, energy absorption or toughness of concrete
- Improves impact resistance, fatigue endurance and shear strength of concrete
- Provides increased ultimate load-bearing capacity which allows possible reduction of concrete section
- Requires less labor to incorporate into concrete than conventional reinforcement
- Offers economical concrete reinforcement solutions with greater project scheduling accuracy
- Ideally suited for pumping or shot placement and thin walled precast products.

PRIMARY APPLICATIONS

- Commercial and light industrial slabs on ground
- Composite metal decks
- Overlays
- Blast-resistant concrete
- Pavements
- Equipment foundations
- Shotcrete

COMPLIANCE

- Conforms to ASTM A820 /A 820M - 04, Type V cold drawn wire
- Conforms to ASTM C 1116/C 1116M, Type I fiber reinforced concrete
- UL Classified: For use as an alternate or in addition to the welded wire fabric used in Floor-Ceiling D700, D800, D900 Series Designs. Fibers may also be used in Floor-Ceiling Design Nos. G229, G243, G256, G514

CHEMICAL AND PHYSICAL PROPERTIES

Fiber Length	38mm (1.5 in) or 50mm (2 in)	Tensile Strength	966 MPa (140 ksi)
Equivalent Diameter	1.14mm (0.045 in)	Anchorage	Continuously deformed circular segment
Aspect Ratio	30 or 44	Material	Low Carbon Steel Wire
Fiber Count, approx	1,500 fibers/lb	Specific Gravity	7.85

PRODUCT USE

MIXING: FRC CSD-2500 steel fibers can be added during or after the batching of the concrete. Such devices as conveyor belts and dispensers may be used to add fibers to the mixer at the ready mix plant. After the addition of the fibers, the concrete should be mixed for a sufficient time (batch plant: minimum 5 minutes or 70 revolutions) at full mixing speed to ensure uniform distribution of the fibers throughout the concrete mix.

PLACING: FRC CSD-2500 steel fibers can be pumped, shot or placed using conventional equipment.

FINISHING: FRC CSD-2500 reinforced concrete can be finished by normal finishing techniques.

APPLICATION RATE: The standard addition rate for FRC CSD-2500 fibers is between 25-66 lbs/yd³. FRC Resources technical staff can offer advice on dosage requirements once performance requirements have been established by the project designer/engineer.

COMPATIBILITY

FRC CSD-2500 fibers are compatible with all concrete admixtures and performance enhancing chemicals.

SAFETY

It is recommended that gloves and eye protection be used when handling or adding FRC CSD-2500 steel fibers to concrete. Full Safety Data Sheets are available on request.

PACKAGING

FRC CSD-2500 fibers are available in 25 kg (55 lb) polyethylene lined paper bags. There are 40 units (2,200 lb) bags on a pallet. The pallets should be protected against rain and snow. Do NOT stack pallets on top of each other.

TECHNICAL SERVICES

Trained FRC Resources fiber specialists are available worldwide to assist and advise in specifications and field service. FRC Resources representatives do not engage in the practice of engineering or supervision of projects and are available solely for service and support of our customers.

REFERENCE DOCUMENTS

- ACI 304 Guide for Measuring, Mixing, Transporting and Placing Concrete
- ACI 506 Guide for Shotcrete
- ACI 544-3R Guide for Specifying, Proportioning, Mixing, Placing and Finishing Steel Fiber Reinforced Concrete.
- ASTM 820 Standard Specification for Steel Fibers for Fiber-Reinforced Concrete.
- ASTM C 94/C 94M Standard Specification for Ready-Mixed Concrete.
- ASTM C1116/C1116M Standard Specification for Fiber-Reinforced Concrete and Shotcrete
- ASTM C 1436 Standard Specification for Materials for Shotcrete
- ASTM C 1550 Standard Test Method for Flexural Toughness of Fiber Reinforced Concrete (Using Centrally Loaded Round Panel)
- ASTM C 1609 /C 1609M Standard Test Method for Flexural Performance of Fiber-Reinforced Concrete (Using Beam With Third-Point Loading)
- Concrete Society (UK) Technical Report 34 Concrete Industrial Floors

SPECIFICATION CLAUSE

Fibers for concrete shall be FRC CSD-2500 steel fibers conforming to ASTM A 820 Type V and manufactured specifically for the reinforcement of concrete. Unless otherwise stated FRC CSD-2500 steel fibers shall be added to the concrete at the batching plant at the recommended application rate of ___ lbs/yd³ and mixed for a sufficient time (min 5 minutes at full mixing speed) to ensure uniform distribution of the fibers throughout the concrete. Fibrous concrete reinforcement shall be supplied by FRC Resources, Seminole, FL. 33772.

Tel: 727.433.4350 Website: www.FRCresources.com

FRC Resources, LLC Seminole, FL 33772 — FRCresources.com
Ed Methfessel: 727.433.4350 — Randy Shelby 407.257.3234

FRC RESOURCES PROVIDES MICRO SYNTHETIC, MARCO SYNTHETIC, STEEL AND BLENDED FIBERS.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, FRC Resources, LLC does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by FRC Resources, LLC for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by FRC Resources, LLC and individual customers. FRC Resources specifically disclaims all other warranties, express or implied including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.